

What Is Claimed Is:

5 1. A pavement treating composition comprising
a quantity of bituminous pavement rejuvenator consisting
essentially of a coal tar derivative containing a mixture
of di-, tri- and tetracyclic aromatic compounds and their
alkyl homologs containing lower alkyl groups together with
a significant amount of phenolic and hydroxy derivatives,
said mixture having a specific gravity at 25/25° C of at
least 1.08, a maximum Brookfield viscosity at 25° C of 30
cps, and an initial boiling point of at least 180° C and a
continuous boiling range to at least 300° C, with 70-40 % by
volume of the material remaining as residue at 300° C, in
admixture with a quantity of a blackening agent.

10 2. The composition according to claim 1 wherein
said blackening agent is one or more of the compositions
selected from the group consisting of soft coal tar pitch,
aromatic cracked petroleum residue, pavement dressing
conditioner, aliphatic amine, aliphatic fatty acid amine,
5 elemental carbon, lampblack, silicone and aromatic cracked
petroleum residue.

4 3. The composition according to claim 1
consisting essentially of: 90.0-99.0 % of said bituminous
pavement rejuvenator, 1.0-10.0 % coal tar pitch (float test
50-300 seconds @ 50° C), 0.001-0.05 silicone and 0-5.0 %
5 aromatic solvents.

Sub
A2

4. The composition according to claim 1 consisting essentially of: 80.0-98.0 % of said bituminous pavement rejuvenator, 2.0-20.0 % pavement dressing conditioner, and 0.001-0.05 % silicone.

5.

The composition according to claim 1 consisting essentially of: 87.0-98.0 % of said bituminous pavement rejuvenator, 2.0-10.0 % coal tar pitch, 0.05-3.0 % amine, and 0.001-0.05 % silicone.

Sub
A3

6. The composition according to claim 1 consisting essentially of: 77.0-98.0 % of said bituminous pavement rejuvenator, 2.0-20.0 % pavement dressing conditioner, 0.05-3.0 % amine, and 0.001-0.05 % silicone.

7.

The composition according to claim 1 consisting essentially of: 92.0-99.0 % bituminous pavement rejuvenator, 0.001-0.05 % silicone, 0.05-3.0 % amine, and 0.01-5.0 % carbon black.

8. A method for blackening pavement, comprising:

admixing a blackening agent into a composition containing a bituminous pavement rejuvenator; and

applying the resulting admixture to the pavement to be treated.

9. The method according to claim 8 wherein said blackening agent is at least one agent selected from the group consisting of soft coal tar pitch, aromatic cracked

Sub
A9 5
petroleum residue, pavement dressing conditioner, aliphatic
amine, aliphatic fatty acid / amine, elemental carbon,
lampblack, silicone and aromatic cracked petroleum residue.

¹¹
~~10~~. The method according to claim ¹⁰ wherein said
blackening agent is a mixture of lampblack, fatty acid
amine and silicone.

ADD
A5